

EARTH

RECYCLING PAPER CLASSIC WHITE



Characteristic	Test-Methods	Unit	tolerance		
			Value	Minimum	Maximum
grammage	ISO 536	g/m ²	80	77	83
moisture relative	—	%	30	25	32
thickness	DIN 20534	µm	103	100	106
opacity	ISO 2471	%	96	96	—
whiteness	ISO 2470	%	72	70	74
water absorption Cobb	DIN EN 20535	g/m ²	25	20	30
breaking length md	DIN EN ISO 1924	m	4500	4500	—
roughness	DIN 53108	ml/min	250	150	350
bending strength	DIN 53121	Nmm	0,13	0,13	—
pH - value	DIN 53124	—	7	6,5	7,5
surface resistance	DIN IEC 60093	Ohm	—	10 ⁸	10 ¹¹
surface strength	ISO 3783	m/s	2	2	—
abrasion resistance	DIN 53109	mg	—	—	20
toner adhesion	DIN EN 12283	—	>0,8	—	—
cut quality	DIN 12281	Anhang C	95% < 5 98% < 6	—	—

additives The additives used are free from organic chlorine compounds and do not lead to AOX formation.

PRIMUS MÜNCHEN GmbH
 Franz-Josef-Strasse 48 • 80 801 München
 Tel.: 089 - 24 24 1810 • Fax: 089 - 24 24 1818
 mail: primus.muenchen@gmail.com
 VAT: DE 321745186



ream
500 sheet



4 260506 230608

carton
5 x 500 sheet



4 260506 230615